

# POLYHEDRON LABORATORIES<sup>®</sup>, INC.

PLASTICS, POLYMERS and RUBBER TESTING

10626 KINGHURST ST. HOUSTON, TX 77099

281-879-8600 • FAX: 281-879-8666

e-mail techsales@polyhedronlab.com

January 15, 2010

ACE Recycled Products  
14925 S. Heritagecrest Way  
Bluffdale, UT 84065

Attn: Mr. Jeremie Paulus

## Analytical Report

### Compressive Strength by ASTM D 695

Sample No. - Wheels

Compressive Strength (lbs)

5415.4

5196.4

6445.6

7039.7


5650.0

4553.7

4108.1

4275.5

AV = 5335.5 ± 1035.3



Howard Kaye, Ph.D., FAIC  
Director

HK/dr

All samples will be discarded within two months.